



**Product**

The electrostatic dissipative polycarbonate sheet provides a permanent protection against electrostatic discharge events (ESD).

EUROPLEX® SDX Glazings dissipate electric charges in a controlled way against earth. EUROPLEX® SDX for planar installations.

Product properties*	Value	Unit	Test method
<b>Electrical</b>			
Surface resistivity	10 <sup>5-7</sup>	Ohm/sq	DIN IEC 60093
<b>Physical</b>			
Density	1,20	g/cm <sup>3</sup>	ISO 1183-1
<b>Optical</b>			
Light transmission factor	85	%	DIN 5033, DIN 5036
Light reflection factor	5	%	DIN 5033, DIN 5036
Haze	3,5	%	ASTM D 1003
<b>Mechanical</b>			
Tensile strength	60	MPa	ISO 527
Modulus of elasticity	2400	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Extensibility	6	%	ISO 527
Nominal elongation	70	%	ISO 527
Bending modulus	2100	MPa	ISO 178
Bending strenght	100	MPa	ISO 178
Bending stress at rupture	no rupture		ISO 178
Bending stress at 3.5 %	80	MPa	ISO 178
Edge fibre elongation at rupture	no rupture		ISO 178
Edge fibre elongation at bending strength	6	%	ISO 178
Compression modulus of elasticity	2400	MPa	ISO 604
Compression strength	70	MPa	ISO 604

Product properties*	Value	Unit	Test method
<b>Mechanical</b>			
Nominal compression at compression strength	8	%	ISO 604
Compression yield stress	70	MPa	ISO 604
Charpy impact strength	no rupture		ISO 179
Charpy notched bar impact strength	11	kJ/m <sup>2</sup>	ISO 179
Abrasion resistance (Taber Abraser)	4	%	ASTM D 1044
<b>Thermal</b>			
Vicat softening point	145	°C	ISO 306
Thermal expansion coefficient	7 x 10 <sup>-5</sup>	1/K	ASTM D 696

\* All data are related to sheets with 3 mm thickness.

**Röhm GmbH**  
Acrylic Products

Riedbahnstraße 70  
64331 Weiterstadt  
Germany

[www.plexiglas.de](http://www.plexiglas.de)  
[www.roehm.com](http://www.roehm.com)

® = registered trademark

EUROPLEX is a registered trademark in EU and a filed trademark in US of Röhm GmbH, Darmstadt, Germany.  
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.